

§ 735.69

for the purpose of the act or the regulations in this part it shall be stated in accordance with §§ 735.68 through 735.73 as far as applicable.

§ 735.69 Official cotton standards of the United States.

The official cotton standards of the United States, established and promulgated under the United States Cotton Standards Act of March 4, 1923 (42 Stat. 1517; 7 U.S.C. 51-56), within their scope, are hereby adopted as the official cotton standards for the purposes of the act and the regulations in this part.

§ 735.70 Defective cotton; designation; terms defined.

(a) Cotton that,

(1) Because of the presence of extraneous matter of any character or irregularities or defects, is reduced in value below that of Good Ordinary,

(2) Is below the grade of Good Ordinary,

(3) Is below the grade of Low Middling, if tinged,

(4) Is below the grade of Middling, if stained,

(5) Is linters,

(6) Is less than seven-eighths of an inch in length of staple,

(7) Is of perished staple,

(8) Is of immature staple,

(9) Is gin cut,

(10) Is reginned,

(11) Is repacked,

(12) Is false packed,

(13) Is mixed packed, or

(14) Is water packed, shall be designated as such.

In the case of paragraph (a)(1) of this section the particular extraneous matter or irregularities or defects shall be stated.

(b) If cotton be reduced in value, by reason of the presence of extraneous matter of any character or irregularities or defects, below its grade or below its apparent length of staple according to the official cotton standards of the United States, the grade or length of staple from which it is so reduced, and the grade or length of staple to which it is so reduced, and the quality or condition which so reduces its value shall be determined and stated.

(c) For the purposes of this section, the following terms shall be construed, respectively, to mean:

7 CFR Ch. VII (1-1-01 Edition)

(1) *Cotton of perished staple.* Cotton that has had the strength of fiber as ordinarily found in cotton destroyed or unduly reduced through exposure to the weather either before picking or after baling, or through heating by fire, or on account of water packing, or by other causes.

(2) *Cotton of immature staple.* Cotton that has been picked and baled before the fiber has reached a normal state of maturity, resulting in a weakened staple of inferior value.

(3) *Gin-cut cotton.* Cotton that shows damage in ginning through cutting by the saws, to an extent that reduces its value more than two grades.

(4) *Reginned cotton.* Cotton that has passed through the ginning process more than once and cotton that, after having been ginned, has been subjected to a cleaning process and then baled.

(5) *Repacked cotton.* Cotton that is composed of factors', brokers', or other samples, or of loose or miscellaneous lots collected and rebaled, or cotton in a bale which is composed of cotton from two or more smaller bales or parts of bales.

(6) *False packed cotton.* Cotton in a bale (i) containing substances entirely foreign to cotton, (ii) containing damaged cotton in the interior with or without any indication of such damage upon the exterior, (iii) composed of good cotton upon the exterior and decidedly inferior cotton in the interior in such manner as not to be detected by customary examination—that is, a plated bale, or (iv) containing pickings or linters worked into the bale.

(7) *Mixed packed cotton.* Cotton in a bale which, in the samples drawn therefrom, shows (i) a difference of three or more grades, or (ii) a difference of three or more color gradations, or (iii) a difference of two or more grades and two or more color gradations, or (iv) a difference in length of staple of one-eighth inch or more.

(8) *Water packed cotton.* Cotton in a bale that has been penetrated by water during the baling process, causing damage to the fiber, or a bale that through exposure to the weather or by other means, while apparently dry on the exterior, has been damaged by water in the interior.