

(2) If the pipe is not tensile tested as provided in paragraph (b)(1) of this section, 24,000 p.s.i. (165 MPa).

[35 FR 13257, Aug. 19, 1970, as amended by Amdt. 192-78, 61 FR 28783, June 6, 1996; Amdt. 192-83, 63 FR 7723, Feb. 17, 1998; Amdt. 192-85, 63 FR 37502, July 13, 1998]

**§ 192.109 Nominal wall thickness (*t*) for steel pipe.**

(a) If the nominal wall thickness for steel pipe is not known, it is determined by measuring the thickness of each piece of pipe at quarter points on one end.

(b) However, if the pipe is of uniform grade, size, and thickness and there are more than 10 lengths, only 10 percent of the individual lengths, but not less than 10 lengths, need be measured. The thickness of the lengths that are not measured must be verified by applying a gauge set to the minimum thickness found by the measurement. The nominal wall thickness to be used in the design formula in §192.105 is the next wall thickness found in commercial specifications that is below the average of all the measurements taken. However, the nominal wall thickness used may not be more than 1.14 times the smallest measurement taken on pipe less than 20 inches (508 millimeters) in outside diameter, nor more than 1.11 times the smallest measurement taken on pipe 20 inches (508 millimeters) or more in outside diameter.

[35 FR 13257, Aug. 19, 1970, as amended by Amdt. 192-85, 63 FR 37502, July 13, 1998]

**§ 192.111 Design factor (*F*) for steel pipe.**

(a) Except as otherwise provided in paragraphs (b), (c), and (d) of this section, the design factor to be used in the design formula in §192.105 is determined in accordance with the following table:

Class location	Design factor ( <i>F</i> )
1 .....	0.72
2 .....	0.60
3 .....	0.50

Class location	Design factor ( <i>F</i> )
4 .....	0.40

(b) A design factor of 0.60 or less must be used in the design formula in §192.105 for steel pipe in Class 1 locations that:

(1) Crosses the right-of-way of an unimproved public road, without a casing;

(2) Crosses without a casing, or makes a parallel encroachment on, the right-of-way of either a hard surfaced road, a highway, a public street, or a railroad;

(3) Is supported by a vehicular, pedestrian, railroad, or pipeline bridge; or

(4) Is used in a fabricated assembly, (including separators, mainline valve assemblies, cross-connections, and river crossing headers) or is used within five pipe diameters in any direction from the last fitting of a fabricated assembly, other than a transition piece or an elbow used in place of a pipe bend which is not associated with a fabricated assembly.

(c) For Class 2 locations, a design factor of 0.50, or less, must be used in the design formula in §192.105 for uncased steel pipe that crosses the right-of-way of a hard surfaced road, a highway, a public street, or a railroad.

(d) For Class 1 and Class 2 locations, a design factor of 0.50, or less, must be used in the design formula in §192.105 for—

(1) Steel pipe in a compressor station, regulating station, or measuring station; and

(2) Steel pipe, including a pipe riser, on a platform located offshore or in inland navigable waters.

[35 FR 13257, Aug. 19, 1970, as amended by Amdt. 192-27, 41 FR 34605, Aug. 16, 1976]

**§ 192.113 Longitudinal joint factor (*E*) for steel pipe.**

The longitudinal joint factor to be used in the design formula in §192.105 is determined in accordance with the following table:

Specification	Pipe class	Longitudinal joint factor ( <i>E</i> )
ASTM A 53 .....	Seamless .....	1.00
	Electric resistance welded .....	1.00
	Furnace butt welded .....	.60

Specification	Pipe class	Longitudinal joint factor (E)
ASTM A 106 .....	Seamless .....	1.00
ASTM A 333/A 333M .....	Seamless .....	1.00
	Electric resistance welded .....	1.00
ASTM A 381 .....	Double submerged arc welded .....	1.00
ASTM A 671 .....	Electric-fusion-welded .....	1.00
ASTM A 672 .....	Electric-fusion-welded .....	1.00
ASTM A 691 .....	Electric-fusion-welded .....	1.00
API 5 L .....	Seamless .....	1.00
	Electric resistance welded .....	1.00
	Electric flash welded .....	1.00
	Submerged arc welded .....	1.00
	Furnace butt welded .....	.60
Other .....	Pipe over 4 inches (102 millimeters) .....	.80
Other .....	Pipe 4 inches (102 millimeters) or less .....	.60

If the type of longitudinal joint cannot be determined, the joint factor to be used must not exceed that designated for “Other.”

[Amdt. 192–37, 46 FR 10159, Feb. 2, 1981, as amended by Amdt. 192–51, 51 FR 15335, Apr. 23, 1986; Amdt. 192–62, 54 FR 5627, Feb. 6, 1989; 58 FR 14521, Mar. 18, 1993; Amdt. 192–85, 63 FR 37502, July 13, 1998]

**§ 192.115 Temperature derating factor (T) for steel pipe.**

The temperature derating factor to be used in the design formula in § 192.105 is determined as follows:

Gas temperature in degrees Fahrenheit (Celsius)	Temperature derating factor (T)
250 °F (121 °C) or less .....	1.000
300 °F (149 °C) .....	0.967
350 °F (177 °C) .....	0.933
400 °F (204 °C) .....	0.900
450 °F (232 °C) .....	0.867

For intermediate gas temperatures, the derating factor is determined by interpolation.

[35 FR 13257, Aug. 19, 1970, as amended by Amdt. 192–85, 63 FR 37502, July 13, 1998]

**§ 192.117 [Reserved]**

**§ 192.119 [Reserved]**

**§ 192.121 Design of plastic pipe.**

Subject to the limitations of § 192.123, the design pressure for plastic pipe is determined in accordance with either of the following formulas:

$$P = 2S \frac{t}{(D - t)} 0.32$$

$$P = \frac{2S}{(SDR - 1)} 0.32$$

Where:

P=Design pressure, gauge, kPa (psig).

S=For thermoplastic pipe, the long-term hydrostatic strength determined in accordance with the listed specification at a temperature equal to 73°F (23°C), 100°F (38°C), 120°F (49°C), or 140°F (60°C); for reinforced thermosetting plastic pipe, 11,000 psi (75,842 kPa).

t=Specified wall thickness, mm (in).

D=Specified outside diameter, mm (in).

SDR=Standard dimension ratio, the ratio of the average specified outside diameter to the minimum specified wall thickness, corresponding to a value from a common numbering system that was derived from the American National Standards Institute preferred number series 10.

[Amdt. 192–78, 61 FR 28783, June 6, 1996, as amended by Amdt. 192–85, 63 FR 37502, July 13, 1998]

**§ 192.123 Design limitations for plastic pipe.**

(a) The design pressure may not exceed a gauge pressure of 689 kPa (100 psig) for plastic pipe used in:

- (1) Distribution systems; or
- (2) Classes 3 and 4 locations.

(b) Plastic pipe may not be used where operating temperatures of the pipe will be:

- (1) Below –20°F (–20°C), or –40°F (–40°C) if all pipe and pipeline components whose operating temperature will be below –29°C (–20°F) have a